

PRODUCT SPECIFICATIONS

Product #	Description	Stake/ Pieces	Stake Size	Approx Lbs. Each
1025	10' x 1/4" x 4"	4	12" x 10ga	35
1025-5	10' x 1/4" x 5"	4	12" x 10ga	44
1025-6	10' x 1/4" x 6"	4	16" x 10ga	52
1025-8	10' x 1/4" x 8"	4	16" x 10ga	67.7
1007	10' x 3/16" x 4"	4	12" x 10ga	25
1007-5	10' x 3/16" x 5"	4	12" x 10ga	32
1007-6	10' x 3/16" x 6"	4	16" x 10ga	38
1007-8	10' x 3/16" x 8"	4	16" x 10ga	51.3
1011	10' x 1/8" x 4"	4	12" x 10ga	17
1011-5	10' x 1/8" x 5"	4	12" x 10ga	23
1011-6	10' x 1/8" x 6"	4	16" x 10ga	27
1011-8	10' x 1/8" x 8"	4	16" x 10ga	34.3
1012	10' x 12ga x 4"	4	12" x 10ga	15
1012-5	10' x 12ga x 5"	4	12" x 10ga	17.3
1012-6	10' x 12ga x 6"	4	16" x 10ga	20
1012-8	10' x 12ga x 8"	4	16" x 10ga	27.6
1014	10' x 14ga x 4"	4	12" x 10ga	11
1014-5	10' x 14ga x 5"	4	12" x 10ga	13.1
1014-6	10' x 14ga x 6"	4	16" x 10ga	15
1014-8	10' x 14ga x 8"	4	16" x 10ga	20.3

DECIMAL THICKNESS RANGE

Product #	Decimal Range
1025	.25 min.
1007	.1875 min.
1011	.125 min.
1012	.0966 to .1126
1014	.0677 to .0817

**Powder Coat Colors (Semi-Gloss or Textured):
Brown, Black, Green
Unpainted and Galvanized edging also available**

STEEL SPECIFICATION

Hot-rolled low/mild carbon steel meets ASTM-A-1011 CS Type B, produced using a modified 1010 chemistry with .08% max carbon. Material is produced with best practices to meet an expected Rockwell B hardness range of 50 to 75.

PAINT APPLICATION

Electrostatically applied powder coat specially formulated to withstand extended outdoor exposure in most cases. This coating is ideally suited and commonly used for lawn and garden equipment, fencing, and playground and recreational equipment.

The information contained here is true and accurate to the best of our knowledge. This information is for specified Colmet products and not for use with any other brand of steel edging. Colmet and Defined By Steel are trademarks and cannot be reproduced without written permission.

